

TECHNICAL DATA

Geocel® HM Silicone

High Modulus Silicone Sealant

Acetoxy Silicone Sealant



Geocel® HM Silicone Sealant is a one-part sealant, which has been specifically developed for use by the sealant contractor. It has good adhesion to a range of non-porous substrates including glass, aluminum and painted wood. Geocel® HM Silicone Sealant is suitable for use in sanitary applications.

BENEFITS

- Specially developed for use by sealant contractors
- High modulus, high elasticity
- Fungus and mildew resistant
- Conforms to ISO 11600
- Resistant to ozone, ultra-violet radiation and temperature extremes.

APPLICATION

Ensure that surfaces to be sealed are clean, dry, sound and free from frost. Clean all joints of release agents, water repellents, laitance, dust, dirt, old sealants and other contaminants, which could impair adhesion. Non-porous surfaces should be cleaned and degreased by wiping with a suitable solvent such as Geocel Surface Cleaner on an oil and lint-free cloth before application of the sealant. Porous substrates should be mechanically cleaned using a steel brush, sanding disc or any similar means.

Note: When using any solvent, always provide adequate ventilation. Avoid heat, sparks and open flames. Use solvent resistant gloves. Observe and follow all precautions listed on solvent container label.

JOINT DESIGN

When designing joints using Geocel® HM, the minimum width should be 6mm. For joints between 6mm-12mm wide, a seal depth of 6mm is required. For joints above 12mm wide, a width to depth ratio of 2:1 should be used up to a maximum depth of 12mm. In situations where fillet joints are needed, a minimum of 6mm sealant bite to each substrate is recommended.

PRIMING

Primer is not required on most common non-porous substrates. However, a test placement prior to general use is always recommended. For specific advice, please refer to the Geocel technical department.

BACK UP MATERIALS

Closed cell polyethylene backer rod is recommended as a back up material to provide back pressure and avoid three-sided adhesion that limits sealant movement capability. Low tack polyethylene tape should be used in joints too shallow to allow the use of backer rod.

FINISHING

The joint should be tooled within 5 minutes of application to ensure good contact between the sealant and the substrate. Tooling of the sealant also gives a smooth, professional finish.

HEALTH AND SAFETY

Health and Safety data sheets available on request.

PACKAGING

Geocel® HM Silicone Sealant is available in 310ml cartridges packed in boxes of 12.

LIMITATIONS

Do not use Geocel® HM Silicone Sealant on bituminous substrates, substrates based on natural rubber, chloroprene or EPDM or on building materials, which might bleed oils, plasticisers or solvents. Do not use Geocel® HM Silicone Sealant in a totally confined space because the sealant requires atmospheric moisture to cure. Because acetic acid is released during curing, it can corrode mirror silver and sensitive metals such as copper, brass and lead. Geocel® HM Silicone sealant is not recommended for use on submerged joints or in joints where physical abuse or abrasion are likely to occur.

Geocel® HM Silicone Sealant is not suitable for food contact applications.

It is recommended that Geocel® HM Silicone Sealant is not applied to surfaces that are below 5°C (41°F) as it is impossible to guarantee a dry surface at these temperatures.

Important Note: The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that Geocel's products are safe, effective and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Geocel's sole warranty is that the product will meet the Geocel sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

Geocel specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability.

Geocel disclaims liability for any incidental or consequential damage.

